



majorpack reziPLY76 coating – protective system based on epoxy phenolic polymer, in majorpack coatings' line-up, designed to protect tubing during operation in corrosive environments.

# reziPLY76

Key features	reziPLY76
Polymeric color	Light-brown
Coating type	Epoxy phenolic
Polymeric thickness	5.6 - 14 mils (140 - 350 microns)*
Anticorrosion properties	Mild H <sub>2</sub> S protection Protection from sweet corrosion (CO <sub>2</sub> ) Abrasion resistance
Exploitation properties	Acid service, pH < 2.5** Alkaline service, pH > 12***
Polymeric temperature, no more than	266°F (130°C)
Short-time polymeric temperature, no more than	392°F (200°C)
Polymeric layer adhesion, not less than	10 MPa

\*  
In accordance with the measurement procedure, established in the manufacturer's QA/QC plan. The measurement procedure can be obtained upon request

\*\*  
10% HCl, t=50°C, duration: 24 hours

\*\*\*  
10% NaOH, t=50°C, duration: 24 hours