



Majorpack ziPLY97 coating – multilayer protection system designed and manufactured for complete protection of tubing; including threads and external surfaces. Especially effective at mitigating asphaltene-resin-paraffin deposits (ARPD).

Key features	ziPLY97
Polymeric color	Beige glossy
Coating type	FeZn Intermetallic + Epoxy phenolic
Tubing intermetallic thickness – inner/outer surface	1.6 - 5 mils (40 - 125 microns)
Polymeric thickness	5.6 - 14 mils (140 - 350 microns)
Tubing thread intermetallic thickness	0.8 - 2.8 mils (20 - 70 microns)
Coating roughness	3 microns
Anticorrosion properties	Protection against high H ₂ S Protection from high sweet corrosion (CO ₂) Protection from ARPD Anti-bacterial protection (SRB, APB) Thread protection Abrasive wear resistance
Acid/alkaline treatments	Acid treatments: pH > 2.5 Alkaline treatments: pH < 12
Polymeric temperature limit, up to	284°F (140°C)
Short-time polymeric temperature limit, up to	392°F (200°C)
Intermetallic temperature limit	572°F (300°C)
Polymeric layer adhesion, not less than, up to	12 MPa

TYPES OF PROTECTION

- Corrosion
- Abrasion
- ARPD

KEY BENEFITS OF MAJORPACK

- ARPD control efficiency
- Corrosion control efficiency
- Cost efficiency
- Ample production capacities
- Reducing carbon footprint
- Ultra-low surface roughness

3 - 18

times is the operation cost reduction depending on the degree of complication

85,000

tons of products are manufactured yearly

18,200

wells in operation globally with majorpack® protective coatings

Get in touch with your local Majorpack representative now and see how we can lower your costs today!

Majorpack Inc.

Energy Corridor, 11111 Katy Freeway,
Suite 910, Houston, TX 77079 USA
Phone: +1 713 973 5761, +1 713 973 57 62
Fax: +1 713 973 5777
Email: info@majorpack.com
web: majorpack.com

We are an emerging leader in industry standards of anti-corrosion coating technology for OCTG. Years of extensive research and product development have demonstrated that multifaceted systems are necessary for complete corrosion protection of downhole tubing.